

ULTRA

SPECIFICATION FOR LINSEED OIL BOILED FOR PAINTS

Description: The material shall be prepared from genuine linseed oil obtained from *Linum usitatissimum* Linn., Fam. Linaceae and necessary dried. It shall be clear and free from sediments and other insoluble matter.

REQUIREMENT FOR LINSEED OIL BOILED FOR PAINTS

S NO.	CHARACTERISTIC	REQUIREMENT FOR	
		Double Boiled	Boiled
i)	Relative density at 30° C/30° C	0.931 to 0.945	0.929 to 0.943
ii)	Acid Value, max	8	6
iii)	Saponification Value	190 to 196	190 to 198
iv)	Unsaponifiable matter, percent by mass, max	2.5	2.0
v)	Drying time, max	12 hours	18 hours
vi)	Ash contents, percent by mass, max	0.5	0.3

PACKING : 200 KGS IN MS DRUMS/ 80 DRUMS PER FCL

ULTRA CHEMICAL WORKS

209 Anantdeep Chambers, 273/277 Narshi Natha Street, Mumbai: 400 009. (India)
Ph: +91 22 66359695 Fax: +91 22 66359694 E-mail: info@ultrachem.co.in
Website : www.ultrachem.co.in